

Tubería Acero



Diametros y Espesores (pulgada)

DIAM. NOM.	DIAM. EXT.	SCH. 10*	SCH. 20	SCH. 30*	STD.	SCH. 40	SCH. 60*	X STRONG	SCH. 80	SCH. 100*	SCH. 120*	SCH. 140*	SCH. 160*	XX STRONG
1/8	0.405	----	----	----	0.068	0.068	----	0.095	0.095	----	----	----	----	----
1/4	0.54	----	----	----	0.088	0.088	----	0.119	0.119	----	----	----	----	----
3/8	0.675	----	----	----	0.091	0.091	----	0.126	0.126	----	----	----	----	----
1/2	0.84	----	----	----	0.109	0.109	----	0.147	0.147	----	----	----	0.187	0.294
3/4	1.05	----	----	----	0.113	0.113	----	0.154	0.154	----	----	----	0.218	0.308
1	1.315	----	----	----	0.133	0.133	----	0.179	0.179	----	----	----	0.25	0.357
1.25	1.66	----	----	----	0.14	0.14	----	0.191	0.191	----	----	----	0.25	0.382
1.5	1.9	----	----	----	0.145	0.145	----	0.2	0.2	----	----	----	0.281	0.4
2	2.375	----	----	----	0.154	0.154	----	0.218	0.218	----	----	----	0.343	0.436
2.5	2.875	----	----	----	0.203	0.203	----	0.276	0.276	----	----	----	0.375	0.552
3	3.5	----	----	----	0.216	0.216	----	0.3	0.3	----	----	----	0.438	0.6
3.5	4	----	----	----	0.226	0.226	----	0.318	0.318	----	----	----	----	0.636
4	4.5	----	----	----	0.237	0.237	----	0.337	0.337	----	0.438	----	0.531	0.674
5	5.563	----	----	----	0.258	0.258	----	0.375	0.375	----	0.5	----	0.625	0.75
6	6.625	----	----	----	0.28	0.28	----	0.432	0.432	----	0.562	----	0.718	0.864
8	8.625	----	0.25	0.277	0.322	0.322	0.406	0.5	0.5	0.593	0.718	0.812	0.906	0.875
10	10.75	----	0.25	0.307	0.365	0.365	0.5	0.5	0.593	0.718	0.843	1	1.125	----
12	12.75	----	0.25	0.33	0.375	0.406	0.562	0.5	0.687	0.843	1	1.125	1.312	----
14 OD	14	0.25	0.312	0.375	0.375	0.438	0.593	0.5	0.75	0.937	1.093	1.25	1.406	----
16 OD	16	0.25	0.312	0.375	0.375	0.5	0.656	0.5	0.843	1.031	1.218	1.438	1.593	----
18 OD	18	0.25	0.375	0.438	0.375	0.562	0.75	0.5	0.937	1.156	1.375	1.562	1.798	----
20 OD	20	0.25	0.375	0.5	0.375	0.593	0.812	0.5	1.031	1.281	1.5	1.75	1.968	----
24 OD	24	0.25	0.375	0.562	0.375	0.687	0.968	0.5	1.218	1.431	1.812	2.062	2.343	----
30 OD	30	0.316	0.5	0.625	0.375	----	----	0.5	----	----	----	----	----	----

Materiales se trabajan contra pedido por importación

Diametros y Pesos (lbs-pie)

DIAM. NOM.	DIAM. EXT.	SCH. 10*	SCH. 20	SCH. 30*	STD.	SCH. 40	SCH. 60*	X STRONG	SCH. 80	SCH. 100*	SCH. 120*	SCH. 140*	SCH. 160*	XX STRONG
1/8	0.405	----	----	----	0.24	0.24	----	0.31	0.31	----	----	----	----	----
1/4	0.54	----	----	----	0.42	0.42	----	0.54	0.54	----	----	----	----	----

3/8	0.675	----	----	----	0.57	0.57	----	0.74	0.74	----	----	----	----	----
1/2	0.84	----	----	----	0.85	0.85	----	1.09	1.09	----	----	----	1.3	1.71
3/4	1.05	----	----	----	1.13	1.13	----	1.47	1.47	----	----	----	1.94	2.44
1	1.315	----	----	----	1.68	1.68	----	2.17	2.17	----	----	----	2.84	3.66
1.25	1.66	----	----	----	2.27	2.27	----	3	3	----	----	----	3.77	5.21
1.5	1.9	----	----	----	2.72	2.72	----	3.63	3.63	----	----	----	4.86	6.41
2	2.375	----	----	----	3.65	3.65	----	5.02	5.02	----	----	----	7.44	9.03
2.5	2.875	----	----	----	5.79	5.79	----	7.66	7.66	----	----	----	10.01	13.7
3	3.5	----	----	----	7.58	7.58	----	10.25	10.25	----	----	----	14.32	18.56
3.5	4	----	----	----	9.11	9.11	----	12.51	12.51	----	----	----	----	22.85
4	4.5	----	----	----	10.79	10.79	----	14.98	14.98	----	19.01	----	22.51	27.54
5	5.563	----	----	----	14.62	14.62	----	20.78	20.78	----	27.04	----	32.96	38.55
6	6.625	----	----	----	18.97	18.97	----	28.57	28.57	----	36.39	----	45.3	53.16
8	8.625	----	22.36	24.7	28.55	28.55	35.64	43.39	43.39	50.87	60.63	67.76	74.69	72.42
10	10.75	----	28.04	34.24	40.48	40.48	54.74	54.74	64.33	76.93	89.2	104.13	115.65	----
12	12.75	----	33.38	43.77	49.56	53.56	73.16	65.42	88.51	107.2	125.49	139.68	160.27	----
14 OD	14	36.71	45.68	54.57	54.57	63.37	84.91	72.09	106.13	130.73	150.67	170.22	189.12	----
16 OD	16	42.05	52.36	62.58	62.58	82.77	107.5	82.77	136.46	164.83	192.29	223.5	245.11	----
18 OD	18	47.39	59.03	82.06	70.59	104.75	138.17	93.45	170.75	207.96	244.14	274.23	308.51	----
20 OD	20	52.73	78.6	104.13	78.6	122.91	166.4	104.13	208.87	256.1	296.37	341.1	379.01	----
24 OD	24	63.41	94.62	140.8	94.62	171.17	230.91	125.49	296.36	367.4	429.39	483.13	541.94	----
30 OD	30	79.43	157.53	196.08	118.65	----	----	157.53	----	----	----	----	----	----

Materiales se trabajan contra pedido por importación



Aliados Agroindustriales, S.A.
Guatemala, Centroamérica
PBX: (502) 2279-0100, 2472-4442 al 49